

boway 51100 SG

Material Designation

Boway designation	boway 51100 SG
UNS	C51100
EN	CuSn4
JIS	C5111
GB(China)	QSn4-0.3

Chemical Composition*

Sn	4	%
Cu	Rem.	


* Nominal composition

Application Target

Signal Connector	Suitable
Power Connector	Not recommend
Miniaturized Connector	Suitable
Switch / Relay	Suitable
Semiconductor	Not recommend

Fabrication Properties

Cold forming	Very good
Machining	Not suitable
Electroplating	Very good
Hot dip tinning	Very good
Laser welding	Good
Resistance welding	Good
Soft soldering	Very good



Characteristics

Very fine microstructure provides excellent bendability and fatigue performance combined with high strength. Replacement for CuSn6. Good corrosion resistance and low sensitivity against stress corrosion cracking as well as excellent solderability.

Physical Properties*

Density	8.8	g/cm ³
Electrical conductivity @ 20°C	19	% IACS
	11	MS/m
Thermal conductivity @ 20°C	100	W/(m·K)
Specific heat capacity	0.377	J/(g·K)
Modulus of elasticity	120	GPa
Poisson's ratio	0.33	
Coefficient of thermal expansion**	17.8	10 ⁻⁶ /K

* Typical values at room temperature for reference.

** average value between 20-300°C

boway 51100 SG

Mechanical Properties

Temper	Tensile strength		Yield strength	Hardness*	Elongation
	MPa	ksi			
R580	580 - 680	84 - 98	≥530	170 - 230	≥13
R660	660 - 760	95 - 110	≥630	180 - 240	≥7
R700	700 - 800	101 - 116	≥690	190 - 250	≥3

*For reference only

Bendability bending thickness: ≤0.4 mm, bending width: 10 mm

Temper	90° R/T		180° R/T	
	Good Way	Bad Way	Good Way	Bad Way
R580	0	0	0	1
R660	0.5	2.5	1.5	3
R700	1	4	—	—

90° bend test According to EN ISO 7438, 180° bend test acc. to ASTM B820, shown values might show orange-peel, however no crack.


Packaging

Standard coils with outside diameter up to 1300 mm,
Traverse-wound coils with drum weight up to 500 kg.
Multiple-coil up to 3 tons.

Dimensions available

Strip thickness 0.08 - 0.4 mm, other gauges on request.
Strip width from 8.5 mm.
Electroplated and Hot-dip tinned strip available

Electrical Conductivity



Fatigue Strength

The fatigue strength is defined as the maximum bending stress amplitude which a material withstands for 10.000.000 load cycles under symmetrical alternate load without breaking. It depends on the temper selected and can be estimated typically by 1/3 of tensile strength. For solid solution fine grain materials fatigue strength might increase up to 0,5 * of tensile strength.