

boway 19000

Material Designation

Boway designation	boway 19000
UNS	C19000
EN	CuNi1P
JIS	--
GB(China)	--

Chemical Composition*

Ni	1.1	%
P	0.25	%
Cu	Rem.	

* Nominal composition


Application Target

Signal Connector	Suitable
Power Connector	Suitable
Miniaturized Connector	Suitable
Switch/Relay	Suitable
Semiconductor	Not recommend

Well suited for USB type-c, particularly for 5G Vapor chamber, relay spring and others.

Fabrication Properties

Cold forming	Good
Machining	Not suitable
Electroplating	Good
Hot dip tinning	Good
Laser welding	Average
Resistance welding	Average
Soft soldering	Good



Characteristics

Superb combination of high conductivity and relatively high strength. Excellent stress relaxation resistance and bending performance. Good corrosion resistance.

Physical Properties*

Density	8.88	g/cm ³
Electrical conductivity @ 20°C	64	% IACS
	37	MS/m
Thermal conductivity @ 20°C	253	W/(m·K)
Specific heat capacity	0.385	J/(g·K)
Modulus of elasticity	130	GPa
Poisson's ratio	0.33	
Coefficient of thermal expansion**	17.6	10 ⁻⁶ /K

* Typical values at room temperature for reference.

** average value between 20-300°C

boway 19000

Mechanical Properties

Temper	Tensile strength		Yield strength	Hardness*	Elongation
	MPa	ksi			
R350(TB00)	≤ 350	≤ 51	≤ 200	≤ 100	≥ 20
R530(TM00)	530 - 620	77 - 90	500 - 600	165 - 200	≥ 4
R580(TM02)	580 - 650	85 - 95	560 - 640	175 - 210	≥ 4
R620(TM04)	620 - 720	90 - 105	600 - 710	180 - 220	≥ 2

*For reference only

Bendability Thickness range: ≤ 0.5 mm , bending width: 10 mm

Temper	90° R/T		180° R/T	
	Good Way	Bad Way	Good Way	Bad Way
R530(TM00)	0.5	1.0	—	—
R580(TM02)	0.5	1.3	—	—
R620(TM04)	1.0	1.7	—	—

90° bend test According to EN ISO 7438, 180° bend test acc. to ASTM B820, shown values might show orange-peel, however no crack.


Packaging

Standard coils with outside diameter up to 1300 mm,
Traverse-wound coils with drum weight up to 500 kg.
Multiple-coil up to 3 tons.

Dimensions available

Strip thickness 0.08 - 2.0 mm, other gauges on request.
Strip width from 10 mm.
Hot-dip tinned and electroplated strip available.

Electrical Conductivity



Fatigue Strength

The fatigue strength is defined as the maximum bending stress amplitude which a material withstands for 10.000.000 load cycles under symmetrical alternate load without breaking. It depends on the temper selected and can be estimated typically by 1/3 of tensile strength. For solid solution fine grain materials fatigue strength might increase up to 0,5 * of tensile strength.